

MG BOARD™ 40KG/M³



NICHIAS

HIGHLY EFFICIENT HIGH TEMPERATURE INSULATION

PRODUCT DATA SHEET

DESCRIPTION

Nichias Rock Wool Insulation is made of inorganic fibres from volcanic rock and minerals bonded together by an organic binder. Using the latest and most advanced manufacturing technology from Japan, ensures consistent product quality, high fibre density and low shot content for excellent performance for high temperature, fire resistance and acoustic applications.

MG Board™ 40kg/m³ is a multi purpose, medium density Rock Wool Board for thermal, acoustic and fire protection applications. The product is available unfaced and with various foil facings including acoustic scrims.

APPLICATIONS

MG Board™ 40kg/m³ provides excellent thermal insulation performance for mechanical/power and process equipment, tanks, ducts, vessels etc.

MG Board™ 40kg/m³ is used for acoustic absorption treatment, personal protection, condensation control and fire protection applications. MG Board™ 40kg/m³ can also be used for its acoustic and R value qualities in commercial roofing, partitioning, ductwork and silencer applications.

MG Board™ 40kg/m³ can be installed by impalling the insulation on welded pins and secured with washers. The unfaced side of the board should be installed to the hot side of the vessel being insulated. MG Board™ 40kg/m³ can also be secured with metal banding or wire.

STANDARD SIZES / PACKAGING / R VALUE

Thickness	Size	pcs Per Pack	R Value @ 24°C
25mm	1.2m x 600mm	20	0.76
40mm	1.2m x 600mm	12	1.2
50mm	1.2m x 600mm	10	1.5
65mm	1.2m x 600mm	7	2.0
75mm	1.2m x 600mm	6	2.3
100mm	1.2m x 600mm	5	3.0



KEY BENEFITS

- * Acoustic Insulation
- * Thermal Insulation
- * High fibre content
- * Low shot content
- * Non combustible
- * Low chloride content as per ASTM C795
- * Safe to use product and meets the criteria for bio solubility
- * Low dust fallout
- * High recycled content
- * Non Corrosive
- * Fire protection
- * Easily cut and formed
- * Does not contain asbestos, CFC, HFC, SCF and HCFC
- * ASTM C612 Mineral fibre block and board thermal insulation - type IV

MG BOARD™ 40KG/M³



NICHIAS

HIGHLY EFFICIENT HIGH TEMPERATURE INSULATION

■ PHYSICAL PROPERTIES

Density (nominal)	40kg/m ³
Thermal Conductivity	ASTM C177 0.33 @ 24°C
Early Fire Hazard	AS1530 Part 3
Ignitability Index	0
Spread of flame	0
Heat evolved	0
Smoke developed	1
Surface Burning Characteristic	ASTM E84
Non Combustible	AS1530 Part 1 BS476 Part 4
Corrosion Resistance	ASTMC795
Water Vapor Absorption	ASTMC1104 Less than 0.02% by volume
Water Absorption	EN 1609
Linear Shrinkage at 650°C	ASTMC356
Shot Content	ASTMC1335
Compressive Strength Test	ASTMC165-07

■ SOUND ABSORPTION PROPERTIES

ASTMC423 Standard test method for sound absorption

Frequency (HZ)	Sound Absorption Co-efficient
100	0.16
125	0.14
250	0.69
500	1.32
1000	1.26
2000	1.03
4000	1.03
5000	0.99
NRC	1.10

* 50mm tested



This product does not contain any asbestos fibres nor freon such as CFCs, HFCs, SCFs, HCFCs, which will affect the environment

■ MANUFACTURER

PT. NICHIAS ROCK WOOL INDONESIA



THERMACON INSULATION

16 HODGSON WAY KEWDALE
PH: +61 08 9353 6033
EMAIL: thermacon@thermacon.com.au



NICHIAS Corporation

<http://www.nichias.co.jp/>

Created 07/04/2020
Revised 12/05/2020